




Detail Gradation Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification
Period 10/25/2018 - 11/01/2018

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	4	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	4	0.3	0.2	0.4	0.2	0.10			
#16 (1.18mm)	4	7.1	5.6	8.8	3.2	1.32			
#30 (0.6mm)	4	32.8	25.3	38.8	13.5	5.59			
#50 (0.3mm)	4	70.7	54.3	76.9	22.6	10.95			
#100 (0.15mm)	4	98.0	95.1	99.1	4.0	1.91			
#200 (75µm)	4	99.9	99.7	100.0	0.3	0.14			
Pan	4	100.0	100.0	100.0	0.0	0.00			
Color	1	4	4	4	0				
Total Moisture	4	3.9	2.7	5.4	2.7	1.12			
FM	4	2.09	1.80	2.24	0.44	0.196			



Comments

Query Query Selections
 Date Created 11/01/2018
 Date Range 10/25/2018 - 11/01/2018
 Plant Independent North Mine (FDOT Pit #11-490)-1050
 Sample Type Shipping