




# Detail Gradation Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 10/25/2018 - 11/01/2018

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	5	0	0	0	0	0.0			
#8 (2.36mm)	5	0	0	0	0	0.0			
#16 (1.18mm)	5	1	1	1	0	0.0			
#30 (0.6mm)	5	8	5	10	5	1.9			
#50 (0.3mm)	5	29	22	32	10	4.2			
#100 (0.15mm)	5	92	90	94	4	1.6			
#200 (75µm)	5	99.9	99.8	100.0	0.2	0.07			
Pan	5	100.0	100.0	100.0	0.0	0.00			
Total Moisture	5	3.4	2.9	3.6	0.7	0.30			
FM	5	1.30	1.17	1.36	0.19	0.076			



**Comments**

**Query** Query Selections  
 Date Created 11/01/2018  
 Date Range 10/25/2018 - 11/01/2018  
 Plant Green Bay Mine (FDOT Pit #16-608)-1130  
 Sample Type Shipping