




Detail Gradation Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification
Period 12/20/2018 - 12/27/2018

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0	0	0	0	0.0			
#8 (2.36mm)	3	0	0	0	0	0.0			
#16 (1.18mm)	3	0	0	0	0	0.0			
#30 (0.6mm)	3	4	3	6	3	1.7			
#50 (0.3mm)	3	39	33	50	17	9.5			
#100 (0.15mm)	3	96	95	97	2	1.0			
#200 (75µm)	3	99.9	99.9	99.9	0.0	0.00			
Pan	2	100.0	100.0	100.0	0.0	0.00			
Total Moisture	3	6.2	4.6	7.4	2.8	1.44			
FM	3	1.39	1.32	1.53	0.21	0.118			



Comments

Query Query Selections
 Date Created 12/27/2018
 Date Range 12/20/2018 - 12/27/2018
 Plant Independent North Mine (FDOT Pit #11-490)-1050
 Sample Type Shipping