




Detail Gradation Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification
Period 12/20/2018 - 12/27/2018

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	4	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	4	0.1	0.0	0.1	0.1	0.05			
#16 (1.18mm)	4	4.5	2.3	7.8	5.5	2.62			
#30 (0.6mm)	4	26.7	16.8	39.4	22.6	11.56			
#50 (0.3mm)	4	55.2	42.9	67.6	24.7	14.06			
#100 (0.15mm)	4	95.8	95.3	96.2	0.9	0.40			
#200 (75µm)	4	99.8	99.5	99.9	0.4	0.19			
Pan	4	100.0	100.0	100.0	0.0	0.00			
Total Moisture	3	4.7	3.7	5.5	1.8	0.91			
FM	4	1.82	1.58	2.11	0.53	0.282			



Comments

Query Query Selections
 Date Created 12/27/2018
 Date Range 12/20/2018 - 12/27/2018
 Plant Green Bay Mine (FDOT Pit #16-608)-1130
 Sample Type Shipping