




# Detail Gradation Statistical Summary Report

**Plant** 2010-Ortona Sand Company (FDOT Pit # 05-045)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 12/20/2018 - 12/27/2018

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0	0	0	0	0.0			
#8 (2.36mm)	3	0	0	0	0	0.0			
#16 (1.18mm)	3	3	2	3	1	0.6			
#30 (0.6mm)	3	24	19	28	9	4.7			
#50 (0.3mm)	3	58	53	61	8	4.4			
#100 (0.15mm)	3	98	97	98	1	0.6			
#200 (75µm)	3	100.0	100.0	100.0	0.0	0.00			
Pan	3	100.0	100.0	100.0	0.0	0.00			
FM	3	1.83	1.72	1.89	0.17	0.095			
Total Moisture	3	4.0	2.9	5.3	2.4	1.21			



**Comments**

**Query** Query Selections  
 Date Created 12/27/2018  
 Date Range 12/20/2018 - 12/27/2018  
 Plant Ortona Sand Company (FDOT Pit # 05-045)-2010  
 Sample Type Shipping