



Independent North Mine (FDOT Pit #11-490)  
8455 C.R. 474  
Clermont, Florida 34714-8339  
352-394-7455

02/01/2019

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	99.6	%	85-100
	#16 (1.18mm)	93.8	%	65-99
	#30 (0.6mm)	72.5	%	25-80
	#50 (0.3mm)	30.7	%	5-40
	#100 (0.15mm)	2.2	%	0-7
	#200 (75µm)	0.0	%	0-4

Sincerely,

Bryan Sanders  
Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-528-2335  
Fax: 352-394-8730