




# Detail Gradation Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1009-Concrete Sand  
**Specification**  
**Period** 03/07/2019 - 03/14/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	4	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	4	0.2	0.1	0.3	0.2	0.10			
#16 (1.18mm)	4	4.7	3.6	5.2	1.6	0.74			
#30 (0.6mm)	4	25.4	22.2	28.0	5.8	2.67			
#50 (0.3mm)	4	72.9	69.1	75.8	6.7	3.23			
#100 (0.15mm)	4	98.7	98.4	99.0	0.6	0.28			
#200 (75µm)	4	100.0	99.9	100.0	0.1	0.06			
Pan	4	100.0	100.0	100.0	0.0	0.00			
Color	1	4	4	4	0				
Total Moisture	4	3.3	2.9	4.1	1.2	0.54			
FM	4	2.02	1.97	2.08	0.11	0.047			



**Comments**

**Query** Query Selections  
 Date Created 03/14/2019  
 Date Range 03/07/2019 - 03/14/2019  
 Plant Independent North Mine (FDOT Pit #11-490)-1050  
 Sample Type Shipping