




Detail Gradation Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification
Period 02/28/2019 - 03/07/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0	0	0	0	0.0			
#8 (2.36mm)	3	0	0	0	0	0.0			
#16 (1.18mm)	3	0	0	0	0	0.0			
#30 (0.6mm)	3	3	1	5	4	2.1			
#50 (0.3mm)	3	35	13	47	34	19.1			
#100 (0.15mm)	3	92	81	98	17	9.8			
#200 (75µm)	3	99.8	99.5	100.0	0.5	0.26			
Pan	3	100.0	100.0	100.0	0.0	0.00			
Total Moisture	3	4.8	4.0	6.5	2.5	1.44			
FM	3	1.31	0.95	1.51	0.56	0.310			



Comments

Query Query Selections
 Date Created 03/07/2019
 Date Range 02/28/2019 - 03/07/2019
 Plant Independent North Mine (FDOT Pit #11-490)-1050
 Sample Type Shipping