




# Detail Gradation Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1009-Concrete Sand  
**Specification**  
**Period** 03/07/2019 - 03/14/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	2	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	2	0.1	0.1	0.1	0.0	0.00			
#16 (1.18mm)	2	5.4	5.1	5.6	0.5	0.35			
#30 (0.6mm)	2	33.4	30.7	36.1	5.4	3.82			
#50 (0.3mm)	2	64.3	62.5	66.1	3.6	2.55			
#100 (0.15mm)	2	97.2	96.7	97.7	1.0	0.71			
#200 (75µm)	2	99.9	99.8	100.0	0.2	0.14			
Pan	2	100.0	100.0	100.0	0.0	0.00			
Total Moisture	2	4.0	2.9	5.2	2.3	1.63			
FM	2	2.00	1.97	2.04	0.07	0.049			



**Comments**

**Query** Query Selections  
 Date Created 03/14/2019  
 Date Range 03/07/2019 - 03/14/2019  
 Plant Green Bay Mine (FDOT Pit #16-608)-1130  
 Sample Type Shipping