




Detail Gradation Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification
Period 05/09/2019 - 05/16/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	5	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	5	0.1	0.0	0.2	0.2	0.07			
#16 (1.18mm)	5	2.8	1.8	4.5	2.7	1.14			
#30 (0.6mm)	5	21.0	17.3	27.9	10.6	4.26			
#50 (0.3mm)	5	76.2	71.2	81.5	10.3	4.08			
#100 (0.15mm)	5	99.1	98.8	99.3	0.5	0.21			
#200 (75µm)	5	99.9	99.8	100.0	0.2	0.09			
Pan	5	100.0	100.0	100.0	0.0	0.00			
Total Moisture	5	3.6	1.9	5.4	3.5	1.36			
FM	5	1.99	1.89	2.13	0.24	0.094			



Comments

Query Query Selections
 Date Created 05/16/2019
 Date Range 05/09/2019 - 05/16/2019
 Plant Independent North Mine (FDOT Pit #11-490)-1050
 Sample Type Shipping