




# Detail Gradation Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 05/09/2019 - 05/16/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0	0	0	0	0.0			
#8 (2.36mm)	3	0	0	0	0	0.0			
#16 (1.18mm)	3	0	0	0	0	0.0			
#30 (0.6mm)	3	1	1	1	0	0.0			
#50 (0.3mm)	3	41	35	47	12	6.0			
#100 (0.15mm)	3	97	97	97	0	0.0			
#200 (75µm)	3	99.9	99.8	100.0	0.2	0.10			
Pan	3	100.0	100.0	100.0	0.0	0.00			
Total Moisture	3	4.5	4.0	4.8	0.8	0.42			
FM	3	1.39	1.34	1.44	0.10	0.050			



**Comments**

**Query** Query Selections  
 Date Created 05/16/2019  
 Date Range 05/09/2019 - 05/16/2019  
 Plant Independent North Mine (FDOT Pit #11-490)-1050  
 Sample Type Shipping