



Independent North Mine (FDOT Pit #11-490)
8455 C.R. 474
Clermont, Florida 34714-8339
352-394-7455

05/01/2019

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (0.6mm)	98	%	
	#50 (0.3mm)	53	%	
	#100 (0.15mm)	2	%	
	#200 (75µm)	0.1	%	

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730