




Detail Gradation Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification
Period 05/09/2019 - 05/16/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	6	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	6	0.2	0.1	0.2	0.1	0.05			
#16 (1.18mm)	6	4.6	2.5	7.1	4.6	1.53			
#30 (0.6mm)	6	32.4	24.9	37.5	12.6	4.74			
#50 (0.3mm)	6	67.0	60.1	75.3	15.2	6.50			
#100 (0.15mm)	6	94.7	92.4	97.7	5.3	1.97			
#200 (75µm)	6	98.6	97.7	99.9	2.2	0.87			
Pan	6	100.0	100.0	100.0	0.0	0.00			
Total Moisture	6	4.9	2.9	6.8	3.9	1.45			
FM	6	1.99	1.82	2.12	0.30	0.111			



Comments

Query Query Selections
 Date Created 05/16/2019
 Date Range 05/09/2019 - 05/16/2019
 Plant Green Bay Mine (FDOT Pit #16-608)-1130
 Sample Type Shipping