



Ortona Sand Company (FDOT Pit # 05-045)
8561 W. State Road 78
Moore Haven, Florida 33975
863-675-3942

05/01/2019

To Whom it may concern,

This material is currently produced at our "Ortona" facility (FDOT mine #05-045) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	
	#8 (2.36mm)	99.9	%	
	#16 (1.18mm)	96.2	%	
	#30 (0.6mm)	52.2	%	
	#50 (0.3mm)	14.4	%	
	#100 (0.15mm)	0.8	%	
	#200 (75µm)	0.0	%	

Sincerely,

Mario Cardenas

Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730