




Detail Gradation Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification
Period 08/29/2019 - 09/05/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	3	0.2	0.2	0.3	0.1	0.06			
#16 (1.18mm)	3	6.4	5.8	7.1	1.3	0.66			
#30 (0.6mm)	3	28.6	27.1	30.7	3.6	1.87			
#50 (0.3mm)	3	66.9	56.0	76.1	20.1	10.16			
#100 (0.15mm)	3	97.4	95.4	99.1	3.7	1.86			
#200 (75µm)	3	99.9	99.9	99.9	0.0	0.00			
Pan	3	100.0	100.0	100.0	0.0	0.00			
Total Moisture	3	5.2	3.0	7.1	4.1	2.06			
FM	3	1.99	1.85	2.09	0.24	0.127			



Comments

Query Query Selections
 Date Created 09/05/2019
 Date Range 08/29/2019 - 09/05/2019
 Plant Independent North Mine (FDOT Pit #11-490)-1050
 Sample Type Shipping