




# Detail Gradation Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 08/29/2019 - 09/05/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0	0	0	0	0.0			
#8 (2.36mm)	3	0	0	0	0	0.0			
#16 (1.18mm)	3	0	0	0	0	0.0			
#30 (0.6mm)	3	2	2	2	0	0.0			
#50 (0.3mm)	3	38	36	39	3	1.5			
#100 (0.15mm)	3	96	96	97	1	0.6			
#200 (75µm)	3	99.9	99.8	100.0	0.2	0.12			
Pan	3	100.0	100.0	100.0	0.0	0.00			
Total Moisture	3	6.9	4.2	9.4	5.2	2.61			
FM	3	1.35	1.34	1.36	0.02	0.012			



**Comments**

**Query** Query Selections  
 Date Created 09/05/2019  
 Date Range 08/29/2019 - 09/05/2019  
 Plant Independent North Mine (FDOT Pit #11-490)-1050  
 Sample Type Shipping