




Detail Gradation Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification
Period 08/29/2019 - 09/05/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	2	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	2	0.1	0.1	0.1	0.0	0.00			
#16 (1.18mm)	2	3.7	3.5	3.9	0.4	0.28			
#30 (0.6mm)	2	23.6	23.1	24.2	1.1	0.78			
#50 (0.3mm)	2	64.0	55.8	72.1	16.3	11.53			
#100 (0.15mm)	2	96.0	95.2	96.7	1.5	1.06			
#200 (75µm)	2	99.8	99.8	99.9	0.1	0.07			
Pan	2	100.0	100.0	100.0	0.0	0.00			
Total Moisture	2	4.4	3.6	5.1	1.5	1.06			
FM	2	1.88	1.81	1.94	0.13	0.092			



Comments

Query Query Selections
 Date Created 09/05/2019
 Date Range 08/29/2019 - 09/05/2019
 Plant Green Bay Mine (FDOT Pit #16-608)-1130
 Sample Type Shipping