




# Detail Gradation Statistical Summary Report

**Plant** 1030-Haines City Mine (FDOT Pit #16-024)  
**Product** 1009-Concrete Sand  
**Specification**  
**Period** 08/29/2019 - 09/05/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	3	0.1	0.0	0.1	0.1	0.06			
#16 (1.18mm)	3	4.6	4.4	4.8	0.4	0.21			
#30 (0.6mm)	3	31.0	30.1	32.6	2.5	1.37			
#50 (0.3mm)	3	57.5	55.9	59.9	4.0	2.12			
#100 (0.15mm)	3	90.4	90.0	90.7	0.7	0.35			
#200 (75µm)	3	99.9	99.9	99.9	0.0	0.00			
Pan	3	100.0	100.0	100.0	0.0	0.00			
FM	3	1.84	1.82	1.87	0.05	0.029			
Total Moisture	3	4.6	3.8	5.4	1.6	0.80			



**Comments**

**Query** Query Selections  
 Date Created 09/05/2019  
 Date Range 08/29/2019 - 09/05/2019  
 Plant Haines City Mine (FDOT Pit #16-024)-1030  
 Sample Type Shipping