




# Detail Gradation Statistical Summary Report

**Plant** 1030-Haines City Mine (FDOT Pit #16-024)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 08/29/2019 - 09/05/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	2	0	0	0	0	0.0			
#8 (2.36mm)	2	0	0	0	0	0.0			
#16 (1.18mm)	2	0	0	0	0	0.0			
#30 (0.6mm)	2	2	2	3	1	0.7			
#50 (0.3mm)	2	14	13	14	1	0.7			
#100 (0.15mm)	2	80	80	81	1	0.7			
#200 (75µm)	2	99.8	99.8	99.8	0.0	0.00			
Pan	2	100.0	100.0	100.0	0.0	0.00			
FM	2	0.97	0.96	0.98	0.02	0.014			
Total Moisture	2	6.4	5.3	7.6	2.3	1.63			



**Comments**

**Query** Query Selections  
 Date Created 09/05/2019  
 Date Range 08/29/2019 - 09/05/2019  
 Plant Haines City Mine (FDOT Pit #16-024)-1030  
 Sample Type Shipping