




# Detail Gradation Statistical Summary Report

**Plant** 2010-Ortona Sand Company (FDOT Pit # 05-045)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 08/29/2019 - 09/05/2019

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	4	0	0	0	0	0.0			
#8 (2.36mm)	4	0	0	0	0	0.0			
#16 (1.18mm)	4	2	1	3	2	1.0			
#30 (0.6mm)	4	29	22	38	16	7.4			
#50 (0.3mm)	4	64	56	74	18	8.9			
#100 (0.15mm)	4	96	95	97	2	1.0			
#200 (75µm)	4	100.0	100.0	100.0	0.0	0.00			
Pan	4	100.0	100.0	100.0	0.0	0.00			
FM	4	1.92	1.76	2.12	0.36	0.179			
Total Moisture	4	3.2	2.8	3.8	1.0	0.45			



**Comments**

**Query** Query Selections  
 Date Created 09/05/2019  
 Date Range 08/29/2019 - 09/05/2019  
 Plant Ortona Sand Company (FDOT Pit # 05-045)-2010  
 Sample Type Shipping