




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1001-FDOT Concrete Silica Sand Code F01  
**Specification** FLDOT Silica Sand  
**Period** 03/19/2020 - 03/26/2020

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	17	100	0.0	95-100	95-100
#8 (2.36mm)	17	100	0.0	85-100	85-100
#16 (1.18mm)	17	93	0.9	67-96	65-97
#30 (0.6mm)	17	64	3.8	27-68	25-70
#50 (0.3mm)	17	21	4.0	7-33	5-35
#100 (0.15mm)	17	3	1.0	0-7	0-7
#200 (75µm)	17	0	0.0	0-4	0-4
Pan	16	0	0.0		
FM	17	2.190	0.0881	2.08-2.4\2.25	2.05-2.45



**Query** Query Selections  
 Date Created 03/26/2020  
 Date Range 03/19/2020 - 03/26/2020  
 Plant Independent South Mine (FDOT Pit#11-298)