




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 03/19/2020 - 03/26/2020

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.6	95-100	
#30 (0.6mm)	4	97	2.1	85-100	
#50 (0.3mm)	4	80	5.5	35-90	
#100 (0.15mm)	4	14	0.5	0-35	
#200 (75µm)	4	0.4	0.06		
Pan	4	0.0	0.00		
FM	4	1.101	0.0818	1.05-1.45\1.2	



**Query** Query Selections  
 Date Created 03/26/2020  
 Date Range 03/19/2020 - 03/26/2020  
 Plant Independent South Mine (FDOT Pit#11-298)