




Detail Gradation Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification
Period 03/19/2020 - 03/26/2020

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	3	0.0	0.0	0.0	0.0	0.00			
#8 (2.36mm)	3	0.1	0.0	0.2	0.2	0.10			
#16 (1.18mm)	3	5.3	4.3	5.8	1.5	0.84			
#30 (0.6mm)	3	33.6	28.1	36.9	8.8	4.82			
#50 (0.3mm)	3	67.0	64.0	68.7	4.7	2.61			
#100 (0.15mm)	3	96.2	95.5	96.5	1.0	0.58			
#200 (75µm)	3	99.8	99.7	99.9	0.2	0.10			
Pan	3	100.0	100.0	100.0	0.0	0.00			
Total Moisture	3	2.5	1.7	3.7	2.0	1.04			
FM	3	2.02	1.92	2.08	0.16	0.090			



Comments

Query Query Selections
 Date Created 03/26/2020
 Date Range 03/19/2020 - 03/26/2020
 Plant Green Bay Mine (FDOT Pit #16-608)-1130
 Sample Type Shipping