



Independent South Mine (FDOT Pit#11-298)
8455 C.R. 474
Clermont, Florida 34714-8339
352-394-7455

09/01/2020

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	99.6	%	85-100
	#16 (1.18mm)	93.9	%	65-99
	#30 (0.6mm)	69.5	%	25-80
	#50 (0.3mm)	31.5	%	5-40
	#100 (0.15mm)	4.0	%	0-7
	#200 (75µm)	0.2	%	0-4
ASTM C-136	FM	2.015		1.85-2.2

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 863-424-0730 ext. 515
Cell: 863-5570342