




Detail Gradation Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/10/2020 - 12/17/2020

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	6	100.0	100.0	100.0	0.0	0.00	95-100		
#8 (2.36mm)	6	99.9	99.8	99.9	0.1	0.05	85-100		
#16 (1.18mm)	6	95.5	94.1	96.6	2.5	0.82	65-97		
#30 (0.6mm)	6	72.5	66.6	75.5	8.9	3.40	25-75		
#50 (0.3mm)	6	42.5	29.5	49.8	20.3	7.44	5-40		
#100 (0.15mm)	6	3.3	1.7	4.5	2.8	0.97	0-7		
#200 (75µm)	6	0.2	0.1	0.5	0.4	0.15			
Pan	6	0.0	0.0	0.0	0.0	0.00			
Total Moisture	6	4.2	3.0	6.5	3.5	1.56	1-5	1-5	67.6
FM	6	1.86	1.75	2.08	0.33	0.120	1.82-2.18\2	1.8-2.2	68.9



Comments

Query Query Selections
 Date Created 12/17/2020
 Date Range 12/10/2020 - 12/17/2020
 Plant Green Bay Mine (FDOT Pit #16-608)
 Sample Type Shipping