




# Detail Gradation Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 12/10/2020 - 12/17/2020

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
#4 (4.75mm)	6	100	100	100	0	0.0	97-100		
#8 (2.36mm)	6	100	100	100	0	0.0	97-100		
#16 (1.18mm)	6	100	100	100	0	0.0	95-100		
#30 (0.6mm)	6	97	95	99	4	1.5	85-100		
#50 (0.3mm)	6	80	75	82	7	2.8	35-90		
#100 (0.15mm)	6	8	6	10	4	1.9	3-35		
#200 (75µm)	6	0.3	0.2	0.6	0.4	0.15			
Pan	6	0.0	0.0	0.0	0.0	0.00			
Total Moisture	6	3.8	2.0	5.7	3.7	1.60	0-5.5	0-6	91.5
FM	6	1.16	1.09	1.24	0.15	0.055	0.9-1.4\1.2		



**Comments**

**Query** Query Selections  
 Date Created 12/17/2020  
 Date Range 12/10/2020 - 12/17/2020  
 Plant Green Bay Mine (FDOT Pit #16-608)  
 Sample Type Shipping