




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 05/04/2021 - 05/11/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.5	0.25		85-100
#16 (1.18mm)	5	93.7	1.49	67-98	65-99
#30 (0.6mm)	5	73.2	3.70	27-79	25-80
#50 (0.3mm)	5	31.1	2.16	7-38	5-40
#100 (0.15mm)	5	2.9	0.69	0-6	0-7
#200 (75µm)	5	0.1	0.04		0-4
Pan	5	0.0	0.00		
<hr/>					
Total Moisture	5	4.3	2.17		
FM	5	2.00	0.062	1.87-2.18\2	1.85-2.2



Query Query Selections
 Date Created 05/11/2021
 Date Range 05/04/2021 - 05/11/2021
 Plant Independent North Mine (FDOT Pit #11-490)
 Sample Type Shipping