




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 05/04/2021 - 05/11/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	95-100	95-100
#8 (2.36mm)	5	99	0.4	85-100	85-100
#16 (1.18mm)	5	92	0.8	67-96	65-97
#30 (0.6mm)	5	65	2.5	27-68	25-70
#50 (0.3mm)	5	24	3.0	7-33	5-35
#100 (0.15mm)	5	2	0.5	0-7	0-7
#200 (75µm)	5	0	0.0	0-4	0-4
Pan	5	0	0.0		
<hr/>					
Total Moisture	3	2.8	0.85		
FM	5	2.17	0.008	2.08-2.4	2.25 2.05-2.45



Query Query Selections
 Date Created 05/11/2021
 Date Range 05/04/2021 - 05/11/2021
 Plant Independent North Mine (FDOT Pit #11-490)
 Sample Type Shipping