




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification
Period 03/18/2021 - 03/25/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	0	0.0		
#8 (2.36mm)	6	0	0.0		
#16 (1.18mm)	6	0	0.0		
#30 (0.6mm)	6	1	0.5		
#50 (0.3mm)	6	31	11.9		
#100 (0.15mm)	6	92	3.6		
#200 (75µm)	6	99.9	0.12		
Pan	6	100.0	0.00		
<hr/>					
Total Moisture	6	6.8	3.39		
FM	6	1.24	0.148		



Query Query Selections
 Date Created 03/25/2021
 Date Range 03/18/2021 - 03/25/2021
 Plant Independent North Mine (FDOT Pit #11-490)-1050
 Sample Type Shipping