




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 05/04/2021 - 05/11/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	95-100	95-100
#8 (2.36mm)	6	99	0.4	85-100	85-100
#16 (1.18mm)	6	92	0.5	67-96	65-97
#30 (0.6mm)	6	57	1.8	27-68	25-70
#50 (0.3mm)	6	22	2.8	7-33	5-35
#100 (0.15mm)	6	3	0.8	0-7	0-7
#200 (75µm)	6	0	0.4	0-4	0-4
Pan	6	0	0.0		
FM	6	2.261	0.0510	2.08-2.4\2.25	2.05-2.45
Total Moisture	6	4.280	0.2644		



Query Query Selections
 Date Created 05/11/2021
 Date Range 05/04/2021 - 05/11/2021
 Plant Independent South Mine (FDOT Pit#11-298)
 Sample Type Shipping