




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 05/04/2021 - 05/11/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.6	0.11		85-100
#16 (1.18mm)	5	93.8	0.89	67-98	65-99
#30 (0.6mm)	5	68.4	4.22	27-79	25-80
#50 (0.3mm)	5	35.6	4.89	7-38	5-40
#100 (0.15mm)	5	5.6	0.97	0-6	0-7
#200 (75µm)	5	0.2	0.11		0-4
Pan	5	0.0	0.00		
FM	5	1.969	0.1078	1.87-2.18\2	1.85-2.2
Total Moisture	5	4.750	0.5257		



Query Query Selections
 Date Created 05/11/2021
 Date Range 05/04/2021 - 05/11/2021
 Plant Independent South Mine (FDOT Pit#11-298)
 Sample Type Shipping