




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 05/04/2021 - 05/11/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	
#8 (2.36mm)	6	99.9	0.04	85-100	
#16 (1.18mm)	6	95.8	0.53	65-99	
#30 (0.6mm)	6	50.8	5.51	25-70	
#50 (0.3mm)	6	12.0	4.10	5-35	
#100 (0.15mm)	6	0.6	0.31	0-7	
#200 (75µm)	6	0.0	0.00		
Pan	6	0.0	0.00		
FM	6	2.41	0.101		
Total Moisture	6	2.6	0.44		



Query Query Selections
 Date Created 05/11/2021
 Date Range 05/04/2021 - 05/11/2021
 Plant Ortona Sand Company (FDOT Pit # 05-045)
 Sample Type Shipping