




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 09/02/2021 - 09/09/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00		95-100
#8 (2.36mm)	4	99.1	0.58		85-100
#16 (1.18mm)	4	91.2	2.49	67-98	65-99
#30 (0.6mm)	4	66.7	3.67	27-79	25-80
#50 (0.3mm)	4	29.6	4.37	7-38	5-40
#100 (0.15mm)	4	3.3	1.86	0-6	0-7
#200 (75µm)	4	0.1	0.10		0-4
Pan	4	0.0	0.00		
<hr/>					
Total Moisture	4	3.2	0.39		
FM	4	2.10	0.045	1.87-2.18\2	1.85-2.2



Query Query Selections
 Date Created 09/09/2021
 Date Range 09/02/2021 - 09/09/2021
 Plant Independent North Mine (FDOT Pit #11-490)
 Sample Type Shipping