




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 09/02/2021 - 09/09/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	0			
#8 (2.36mm)	1	0			
#16 (1.18mm)	1	0			
#30 (0.6mm)	1	13			
#50 (0.3mm)	1	26			
#100 (0.15mm)	1	80			
#200 (75µm)	1	99.9			
Pan	1	100.0			
<hr/>					
Total Moisture	1	5.7			
FM	1	1.19			



**Query** Query Selections  
 Date Created 09/09/2021  
 Date Range 09/02/2021 - 09/09/2021  
 Plant Independent North Mine (FDOT Pit #11-490)-1050  
 Sample Type Shipping