




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 09/02/2021 - 09/09/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00		95-100
#8 (2.36mm)	4	99.5	0.00		85-100
#16 (1.18mm)	4	93.3	0.39	67-98	65-99
#30 (0.6mm)	4	68.7	1.83	27-79	25-80
#50 (0.3mm)	4	31.6	3.80	7-38	5-40
#100 (0.15mm)	4	3.6	0.77	0-6	0-7
#200 (75µm)	4	0.1	0.05		0-4
Pan	4	0.0	0.00		
FM	4	2.033	0.0640	1.87-2.18\2	1.85-2.2



**Query** Query Selections  
 Date Created 09/09/2021  
 Date Range 09/02/2021 - 09/09/2021  
 Plant Independent South Mine (FDOT Pit#11-298)  
 Sample Type Shipping