




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1008-Mason Sand
Specification Mason Sand
Period 09/02/2021 - 09/09/2021

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|---------------|-------|---------|--------|-----------|---------------|
| #4 (4.75mm) | 4 | 100 | 0.0 | 97-100 | |
| #8 (2.36mm) | 4 | 100 | 0.0 | 97-100 | |
| #16 (1.18mm) | 4 | 100 | 0.6 | 95-100 | |
| #30 (0.6mm) | 4 | 96 | 3.0 | 85-100 | |
| #50 (0.3mm) | 4 | 84 | 5.9 | 35-90 | |
| #100 (0.15mm) | 4 | 18 | 3.4 | 0-35 | |
| #200 (75µm) | 4 | 0.5 | 0.21 | | |
| Pan | 4 | 0.0 | 0.00 | | |
| FM | 4 | 1.027 | 0.1185 | 1.05-1.45 | 1.2 |



Query Query Selections
 Date Created 09/09/2021
 Date Range 09/02/2021 - 09/09/2021
 Plant Independent South Mine (FDOT Pit#11-298)
 Sample Type Shipping