




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 09/02/2021 - 09/09/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	
#8 (2.36mm)	5	99.9	0.05	85-100	
#16 (1.18mm)	5	95.3	0.97	65-99	
#30 (0.6mm)	5	53.9	5.22	25-70	
#50 (0.3mm)	5	21.8	3.79	5-35	
#100 (0.15mm)	5	2.3	0.16	0-7	
#200 (75µm)	5	0.0	0.00		
Pan	5	0.0	0.00		
FM	5	2.27	0.100		
Total Moisture	5	3.8	1.13		



Query Query Selections
 Date Created 09/09/2021
 Date Range 09/02/2021 - 09/09/2021
 Plant Ortona Sand Company (FDOT Pit # 05-045)
 Sample Type Shipping