




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification
Period 10/28/2021 - 11/04/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	0			
#8 (2.36mm)	1	0			
#16 (1.18mm)	1	0			
#30 (0.6mm)	1	2			
#50 (0.3mm)	1	11			
#100 (0.15mm)	1	86			
#200 (75µm)	1	99.5			
Pan	1	100.0			
<hr/>					
Total Moisture	1	11.2			
FM	1	0.99			



Query Query Selections
 Date Created 11/04/2021
 Date Range 10/28/2021 - 11/04/2021
 Plant Independent North Mine (FDOT Pit #11-490)-1050
 Sample Type Shipping