



Independent South Mine (FDOT Pit#11-298)
8455 C.R. 474
Clermont, Florida 34714-8339
352-394-7455

11/01/2021

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

1009-Concrete Sand

| Procedure | Sieve/Test | Average | Unit | Concrete Sand |
|------------|---------------|---------|------|---------------|
| | #4 (4.75mm) | 100.0 | % | 95-100 |
| | #8 (2.36mm) | 99.5 | % | 85-100 |
| | #16 (1.18mm) | 93.7 | % | 65-99 |
| | #30 (0.6mm) | 69.8 | % | 25-80 |
| | #50 (0.3mm) | 32.0 | % | 5-40 |
| | #100 (0.15mm) | 3.8 | % | 0-7 |
| | #200 (75µm) | 0.2 | % | 0-4 |
| ASTM C-136 | FM | 2.011 | | 1.85-2.2 |

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 863-424-0730 ext. 515
Cell: 863-5570342