




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 10/28/2021 - 11/04/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.4	0.11		85-100
#16 (1.18mm)	5	92.8	0.94	67-98	65-99
#30 (0.6mm)	5	67.3	4.09	27-79	25-80
#50 (0.3mm)	5	29.6	5.74	7-38	5-40
#100 (0.15mm)	5	3.6	1.26	0-6	0-7
#200 (75µm)	5	0.1	0.04		0-4
Pan	5	0.0	0.00		
FM	5	2.074	0.1188	1.87-2.18\2	1.85-2.2



**Query** Query Selections  
 Date Created 11/04/2021  
 Date Range 10/28/2021 - 11/04/2021  
 Plant Independent South Mine (FDOT Pit#11-298)  
 Sample Type Shipping