




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/28/2021 - 11/04/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00	95-100	
#8 (2.36mm)	4	99.9	0.00	85-100	
#16 (1.18mm)	4	94.8	0.79	65-97	
#30 (0.6mm)	4	67.6	4.04	25-75	
#50 (0.3mm)	4	33.8	4.10	5-40	
#100 (0.15mm)	4	2.4	0.42	0-7	
#200 (75µm)	4	0.0	0.05		
Pan	4	0.0	0.00		
Total Moisture	4	4.2	1.20	1-5	1-5
FM	4	2.01	0.084	1.82-2.18\2	1.8-2.2



Query Query Selections
 Date Created 11/04/2021
 Date Range 10/28/2021 - 11/04/2021
 Plant Green Bay Mine (FDOT Pit #16-608)
 Sample Type Shipping