



Green Bay Mine (FDOT Pit #16-608)  
4949 Sand Mine Road  
Davenport, Florida 33897  
863-424-0730

11/01/2021

To Whom it may concern,

This material is currently produced at our "Green Bay" facility (FDOT mine #16-608) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	
	#8 (2.36mm)	99.9	%	
	#16 (1.18mm)	94.9	%	
	#30 (0.6mm)	68.3	%	
	#50 (0.3mm)	37.3	%	
	#100 (0.15mm)	3.1	%	
	#200 (75µm)	0.1	%	

Sincerely,

**Mario Cardenas**

Quality Control Manager

E.R. Jahna Ind, Inc.

Office: 352-394-7455

Cell: 863-557-0342

Fax: 352-394-8730