




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/28/2021 - 11/04/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	
#8 (2.36mm)	5	99.9	0.00	85-100	
#16 (1.18mm)	5	95.0	0.97	65-99	
#30 (0.6mm)	5	43.6	4.64	25-70	
#50 (0.3mm)	5	7.2	1.74	5-35	
#100 (0.15mm)	5	0.4	0.13	0-7	
#200 (75µm)	5	0.0	0.00		
Pan	5	0.0	0.00		
FM	5	2.54	0.071		
Total Moisture	5	2.5	0.86		



Query Query Selections
 Date Created 11/04/2021
 Date Range 10/28/2021 - 11/04/2021
 Plant Ortona Sand Company (FDOT Pit # 05-045)
 Sample Type Shipping