




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 12/09/2021 - 12/16/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	2	0	0.0		
#8 (2.36mm)	2	0	0.0		
#16 (1.18mm)	2	0	0.0		
#30 (0.6mm)	2	2	0.7		
#50 (0.3mm)	2	12	2.1		
#100 (0.15mm)	2	83	1.4		
#200 (75µm)	2	99.4	0.07		
Pan	2	100.0	0.00		
<hr/>					
Total Moisture	2	6.6	0.57		
FM	2	0.98	0.049		



**Query** Query Selections  
 Date Created 12/16/2021  
 Date Range 12/09/2021 - 12/16/2021  
 Plant Independent North Mine (FDOT Pit #11-490)-1050  
 Sample Type Shipping