



Independent South Mine (FDOT Pit#11-298)  
8455 C.R. 474  
Clermont, Florida 34714-8339  
352-394-7455

01/01/2022

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (0.6mm)	100	%	
	#50 (0.3mm)	97	%	
	#100 (0.15mm)	24	%	
	#200 (75µm)	0.7	%	
ASTM C-136	FM	0.799		

Sincerely,

Mario Cardenas  
Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 863-424-0730 ext.515  
Cell: 863-557-0342