




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 12/23/2021 - 12/30/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	97-100	
#8 (2.36mm)	3	100	0.0	97-100	
#16 (1.18mm)	3	100	0.0	95-100	
#30 (0.6mm)	3	99	0.0	85-100	
#50 (0.3mm)	3	81	1.7	35-90	
#100 (0.15mm)	3	6	0.6	3-35	
#200 (75µm)	3	0.1	0.06		
Pan	3	0.0	0.00		
Total Moisture	3	4.2	0.55	0-5.5	0-6
FM	3	1.14	0.015	0.9-1.4\1.2	



Query Query Selections
 Date Created 12/30/2021
 Date Range 12/23/2021 - 12/30/2021
 Plant Green Bay Mine (FDOT Pit #16-608)
 Sample Type Shipping