




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 12/27/2021 - 01/04/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100	0.0	95-100	95-100
#8 (2.36mm)	8	98	0.5	85-100	85-100
#16 (1.18mm)	8	88	1.1	67-96	65-97
#30 (0.6mm)	8	63	3.5	27-68	25-70
#50 (0.3mm)	8	32	7.6	7-33	5-35
#100 (0.15mm)	8	2	1.1	0-7	0-7
#200 (75µm)	8	0	0.0	0-4	0-4
Pan	7	0	0.0		
Grad Loss	8	0.068	0.0833		
-#200 (75um)	1	0.09			
Wash Loss (#200/75um)	1	0.06			
Color	1	4		1-5\3	1-5
Total Moisture	7	3.2	0.40		
FM	8	2.16	0.120	2.08-2.4\2.25	2.05-2.45



Query Query Selections
 Date Created 01/04/2022
 Date Range 12/27/2021 - 01/04/2022
 Plant Independent North Mine (FDOT Pit #11-490)