




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/23/2021 - 12/30/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00		95-100
#8 (2.36mm)	4	99.5	0.17		85-100
#16 (1.18mm)	4	94.4	1.31	67-98	65-99
#30 (0.6mm)	4	72.5	4.00	27-79	25-80
#50 (0.3mm)	4	34.3	3.28	7-38	5-40
#100 (0.15mm)	4	3.8	1.01	0-6	0-7
#200 (75µm)	4	0.1	0.05		0-4
Pan	4	0.0	0.00		
FM	4	1.955	0.0945	1.87-2.18\2	1.85-2.2



Query Query Selections
 Date Created 12/30/2021
 Date Range 12/23/2021 - 12/30/2021
 Plant Independent South Mine (FDOT Pit#11-298)
 Sample Type Shipping