




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/23/2021 - 12/30/2021

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	
#8 (2.36mm)	5	99.9	0.05	85-100	
#16 (1.18mm)	5	95.8	2.72	65-99	
#30 (0.6mm)	5	55.0	18.58	25-70	
#50 (0.3mm)	5	17.5	12.96	5-35	
#100 (0.15mm)	5	1.9	1.57	0-7	
#200 (75µm)	5	0.0	0.00		
Pan	5	0.0	0.00		
FM	5	2.30	0.358		
Total Moisture	5	2.9	0.57		



Query Query Selections
 Date Created 12/30/2021
 Date Range 12/23/2021 - 12/30/2021
 Plant Ortona Sand Company (FDOT Pit # 05-045)
 Sample Type Shipping