




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FDOT Concrete Silica Sand Code F01
Period 12/27/2021 - 01/04/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100.0	0.00		95-100
#8 (2.36mm)	8	99.9	0.05		85-100
#16 (1.18mm)	8	94.8	0.31	67-96	65-97
#30 (0.6mm)	8	44.8	1.55	27-68	25-70
#50 (0.3mm)	8	9.8	2.31		5-35
#100 (0.15mm)	8	0.9	0.69		0-7
#200 (75µm)	8	0.0	0.04		
Pan	8	0.0	0.00		
-#200 (75µm)	1	0.06			
Grad Loss	8	0.004	0.0113		
Color	1	3		1-2.5\1	1-3
Wash Loss (#200/75µm)	1	0.06			
FM	8	2.50	0.036	2.22-2.57\2.4	2.2-2.6
Total Moisture	7	3.3	0.47		



Query Query Selections
 Date Created 01/04/2022
 Date Range 12/27/2021 - 01/04/2022
 Plant Ortona Sand Company (FDOT Pit # 05-045)
 Sample Type Shipping